



ArmorSeal
Heavy Duty
Floor
Coatings

8.22

ARMORSEAL® 1000 HS

PART A B67-2000
PART B B67V2002

SERIES
HARDENER

PRODUCT INFORMATION

Revised 4/06

PRODUCT DESCRIPTION	RECOMMENDED USES																																								
<p>ARMORSEAL 1000 HS is a high solids, heavy duty, two-component, catalyzed, polyamide epoxy coating formulated for demanding marine and industrial requirements. This dries rapidly to a tough, high gloss finish with excellent resistance to alkalis, abrasion, corrosion, and chemical attack.</p> <ul style="list-style-type: none"> • Chemical Resistant • Impact Resistant • Abrasion Resistant 	<ul style="list-style-type: none"> • For industrial, commercial, or marine applications where a heavy duty epoxy coating is required. • Superior resistance to chemicals, moisture, abrasion, and impact • Meets ADA requirements for slip resistance for floors • Excellent resistance to alkalis, dilute acids, spillage of solvents, chemicals, jet fuel, grease, etc. • Clear finish for interior use only • Suitable for use in USDA inspected facilities 																																								
PRODUCT CHARACTERISTICS	PERFORMANCE CHARACTERISTICS																																								
<p>Finish: Gloss</p> <p>Color: Clear, Haze Gray, Deck Gray, White, Sandstone, Tile Red, Safety Yellow, and a wide range of tinted colors</p> <p>Volume Solids, mixed: colors—65% ± 2% may vary by color clear—61% ± 2%</p> <p>Weight Solids, mixed: 74% ± 2%, may vary by color</p> <p>VOC (EPA Method 24), mixed, may vary by color: colors Unreduced: <340 g/L; 2.8 lb/gal clear <400 g/L; 3.33 lb/gal</p> <p>Mix Ratio: 1:1 by volume</p> <p>Recommended Spreading Rate per coat: Wet mils: 5.0 - 8.0 Dry mils: 3.0 - 5.0 Coverage: 206 - 350 sq ft/gal approximate</p> <p>NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.</p> <p>Drying Schedule @ 6.0 mils wet @ 50% RH:</p> <table border="1"> <thead> <tr> <th></th> <th>@ 50°F</th> <th>@ 77°F</th> <th>@ 120°F</th> </tr> </thead> <tbody> <tr> <td>To touch:</td> <td>4 hours</td> <td>2 hours</td> <td>30 minutes</td> </tr> <tr> <td>To recoat:</td> <td></td> <td></td> <td></td> </tr> <tr> <td> minimum:</td> <td>24 hours</td> <td>8 hours</td> <td>4 hours</td> </tr> <tr> <td> maximum:</td> <td>7 days</td> <td>7 days</td> <td>7 days</td> </tr> <tr> <td>Foot traffic:</td> <td>48 hours</td> <td>24 hours</td> <td>12 hours</td> </tr> <tr> <td>Heavy Traffic:</td> <td>4-5 days</td> <td>48-72 hrs</td> <td>24-36 hrs</td> </tr> <tr> <td>To cure:</td> <td>10 days</td> <td>7 days</td> <td>4 days</td> </tr> <tr> <td>Pot Life:</td> <td>6 hours</td> <td>4 hours</td> <td>2 hours</td> </tr> <tr> <td>Sweat-in-Time:</td> <td>2 hours</td> <td>30 minutes</td> <td>10 minutes</td> </tr> </tbody> </table> <p>If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.</p> <p>Shelf Life: 36 months, unopened Store indoors at 40°F to 100°F.</p> <p>Flash Point: 105°F, Seta, mixed</p> <p>Reducer/Clean Up: Reducer #54, R7K54</p>		@ 50°F	@ 77°F	@ 120°F	To touch:	4 hours	2 hours	30 minutes	To recoat:				minimum:	24 hours	8 hours	4 hours	maximum:	7 days	7 days	7 days	Foot traffic:	48 hours	24 hours	12 hours	Heavy Traffic:	4-5 days	48-72 hrs	24-36 hrs	To cure:	10 days	7 days	4 days	Pot Life:	6 hours	4 hours	2 hours	Sweat-in-Time:	2 hours	30 minutes	10 minutes	<p>System Tested: (unless otherwise indicated) Substrate: Concrete Surface Preparation: Clean, dry, sound 1 ct. ArmorSeal 1000 HS (reduced) 1 ct. ArmorSeal 1000 HS @ 3.0 - 5.0 mils dft</p> <p>Abrasion Resistance: Method: ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load Result: 64.8 mg loss</p> <p>Adhesion, over concrete: Method: ASTM D4541 Result: 350 psi, 100% concrete failure</p> <p>Direct Impact Resistance (steel): Method: ASTM D2794 Result: 58 in. lbs</p> <p>Dry Heat Resistance: Method: ASTM D2485 Result: 180°F</p> <p>Flexibility (steel): Method: ASTM D522, 180° bend, 1/8" mandrel Result: Passes</p> <p>Pencil Hardness: Method: ASTM D3363 Result: HB</p> <p>Slip Resistance, Floors: Method: ASTM C1028-96, .60 minimum Static Coefficient of Friction Result: Passes wet and dry, with and without SharkGrip Additive</p> <p>Epoxy coatings may darken or yellow following application and curing.</p>
	@ 50°F	@ 77°F	@ 120°F																																						
To touch:	4 hours	2 hours	30 minutes																																						
To recoat:																																									
minimum:	24 hours	8 hours	4 hours																																						
maximum:	7 days	7 days	7 days																																						
Foot traffic:	48 hours	24 hours	12 hours																																						
Heavy Traffic:	4-5 days	48-72 hrs	24-36 hrs																																						
To cure:	10 days	7 days	4 days																																						
Pot Life:	6 hours	4 hours	2 hours																																						
Sweat-in-Time:	2 hours	30 minutes	10 minutes																																						



ArmorSeal
Heavy Duty
Floor
Coatings

8.22

ARMORSEAL® 1000 HS

PART A B67-2000
PART B B67V2002

SERIES
HARDENER

PRODUCT INFORMATION

RECOMMENDED SYSTEMS	SURFACE PREPARATION
<p>Concrete/Wood: 1 ct. ArmorSeal 1000 HS (reduced as necessary up to 1 pt/gal with R7K54)* 1-2 cts. ArmorSeal 1000 HS @ 3.0 - 5.0 mils dft/ct (with anti-slip aggregate if required)</p> <p>Concrete: 1 ct. ArmorSeal 33 Epoxy Primer/Sealer @ 8.0 mils dft 1-2 cts. ArmorSeal 1000 HS @ 3.0 - 5.0 mils dft/ct (with anti-slip aggregate if required)</p> <p>Steel: 1 ct. Recoatable Epoxy Primer @ 4.0 - 5.0 mils dft 1-2 cts. ArmorSeal 1000 HS @ 3.0 - 5.0 mils dft/ct</p> <p>Painted Surfaces in Sound Condition: 1-2 cts. ArmorSeal 1000 HS @ 3.0 - 5.0 mils dft/ct</p> <p>*Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.</p> <p>The systems listed above are representative of the products use, other systems may be appropriate.</p>	<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Refer to product Application Bulletin for detailed surface preparation information.</p> <p>Minimum recommended surface preparation: * Iron & Steel: SSPC-SP6/NACE 3 Concrete & Masonry: SSPC-SP13/NACE 6, or ICRI 03732, CSP 1-3 Wood, interior: Clean, smooth, dust free * Primer Required</p>
	<p style="text-align: center;">TINTING</p> <p>White may be tinted using 844 Colorants at 200% tinting strength, 8 oz per gallon maximum, into Part A. Five minutes minimum mixing on a mechanical shaker is required for complete mixing of color.</p>
	<p style="text-align: center;">APPLICATION CONDITIONS</p> <p>Temperature: 50°F minimum, 120°F maximum (air, surface, and material) At least 5°F above dew point Relative humidity: 85% maximum</p> <p>Refer to product Application Bulletin for detailed application information.</p>
	<p style="text-align: center;">ORDERING INFORMATION</p> <p>Packaging: Part A: 1 gallon containers Part B: 1 gallon containers (clear available in 5 gallon containers)</p> <p>Weight per gallon: 12.51 ± 0.2 lb mixed, may vary by color</p>
	<p style="text-align: center;">SAFETY PRECAUTIONS</p> <p>Refer to the MSDS sheet before use.</p> <p>Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.</p>
<p style="text-align: center;">DISCLAIMER</p>	<p style="text-align: center;">WARRANTY</p>
<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</p>	<p>The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.</p>



ArmorSeal
Heavy Duty
Floor
Coatings

8.22A

ARMORSEAL® 1000 HS

PART A B67-2000
PART B B67V2002

SERIES
HARDENER

APPLICATION BULLETIN

Revised 4/06

SURFACE PREPARATION	APPLICATION CONDITIONS
<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Iron & Steel (atmospheric service) Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Commercial Blast Cleaning per SSPC-SP6/NACE 3. For better performance, use Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils). Prime any bare steel the same day as it is cleaned or before flash rusting occurs.</p>	<p>Temperature: 50°F minimum, 120°F maximum (air, surface, and material) At least 5°F above dew point</p> <p>Relative humidity: 85% maximum</p>
<p>Poured Concrete New For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI 03732, CSP 1-3. Surfaces must be clean, dry, sound and offer sufficient profile to achieve adequate adhesion. Minimum substrate cure is 28 days at 75°F. Remove all form release agents, curing compounds, salts, efflorescence, laitance, and other foreign matter by sandblasting, shotblasting, mechanical scarification, or suitable chemical means. Refer to ASTM D4260. Rinse thoroughly to achieve a final pH between 8.0 and 10.0. Allow to dry thoroughly prior to coating.</p> <p>Old Surface preparation is done in much the same manner as new concrete, however, if the concrete is contaminated with oils, grease, chemicals, etc., they must be removed by cleaning with a strong detergent. Refer to ASTM D4258. Form release agents, hardeners, etc. must be removed by sandblasting, shotblasting, mechanical scarification, or suitable chemical means. If surface deterioration presents an unacceptably rough surface, ArmorSeal 5020 Floor Resurfacer is recommended to patch and resurface damaged concrete. Fill all cracks, voids and bugholes with ArmorSeal Crack Filler.</p> <p>Always follow the standard methods listed below: ASTM D4258 Standard Practice for Cleaning Concrete. ASTM D4259 Standard Practice for Abrading Concrete. ASTM D4260 Standard Practice for Etching Concrete. ASTM F1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete. SSPC-SP 13/Nace 6 Surface Preparation of Concrete ICRI 03732 Concrete Surface Preparation</p> <p>Previously Painted Surfaces If in sound condition, clean the surface of all foreign material. Smooth, hard or glossy coatings and surfaces should be dulled by abrading the surface. Apply a test area, allowing paint to dry one week before testing adhesion. If adhesion is poor, or if this product attacks the previous finish, removal of the previous coating may be necessary. If paint is peeling or badly weathered, clean surface to sound substrate and treat as a new surface as above.</p>	<p>APPLICATION EQUIPMENT</p> <p>The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.</p> <p>Reducer/Clean Up Reducer #54, R7K54</p> <p>Airless Spray Pressure 2500 psi Hose 3/8" ID Tip015" - .021" Filter 60 mesh Reduction As needed up to 10% by volume</p> <p>Brush Nylon/Polyester or Natural Bristle Reduction As needed up to 10% by volume</p> <p>Roller Cover 3/8" woven with phenolic core Reduction As needed up to 10% by volume</p> <p>If specific application equipment is not listed above, equivalent equipment may be substituted.</p>



ArmorSeal
Heavy Duty
Floor
Coatings

8.22A

ARMORSEAL® 1000 HS

PART A B67-2000
PART B B67V2002

SERIES
HARDENER

APPLICATION BULLETIN

APPLICATION PROCEDURES	PERFORMANCE TIPS																																
<p>Surface preparation must be completed as indicated.</p> <p>Mix contents of each component thoroughly with a variable speed drill with a metal mixing blade (Jiffy Model HS or equal). Combine one Part A with one Part B by volume and mix for 3 minutes and until uniform. Allow the material to sweat-in as indicated. Re-stir before using.</p> <p>Apply paint at the recommended film thickness and spreading rate as indicated below:</p> <p>Recommended Spreading Rate per coat: Wet mils: 5.0 - 8.0 Dry mils: 3.0 - 5.0 Coverage: 206 - 350 sq ft/gal approximate</p> <p>NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.</p> <p>Drying Schedule @ 6.0 mils wet @ 50% RH:</p> <table border="1"> <thead> <tr> <th></th> <th>@ 50°F</th> <th>@ 77°F</th> <th>@ 120°F</th> </tr> </thead> <tbody> <tr> <td>To touch:</td> <td>4 hours</td> <td>2 hours</td> <td>30 minutes</td> </tr> <tr> <td>To recoat:</td> <td></td> <td></td> <td></td> </tr> <tr> <td> minimum:</td> <td>24 hours</td> <td>8 hours</td> <td>4 hours</td> </tr> <tr> <td> maximum:</td> <td>7 days</td> <td>7 days</td> <td>7 days</td> </tr> <tr> <td>Foot traffic:</td> <td>48 hours</td> <td>24 hours</td> <td>12 hours</td> </tr> <tr> <td>Heavy Traffic hours:</td> <td>4-5 days</td> <td>48-72 hours</td> <td>24-36</td> </tr> <tr> <td>To cure:</td> <td>10 days</td> <td>7 days</td> <td>4 days</td> </tr> </tbody> </table> <p>Pot Life: 6 hours 4 hours 2 hours</p> <p>Sweat-in-Time: 2 hours 30 minutes 10 minutes</p> <p>If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.</p> <p>Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.</p>		@ 50°F	@ 77°F	@ 120°F	To touch:	4 hours	2 hours	30 minutes	To recoat:				minimum:	24 hours	8 hours	4 hours	maximum:	7 days	7 days	7 days	Foot traffic:	48 hours	24 hours	12 hours	Heavy Traffic hours:	4-5 days	48-72 hours	24-36	To cure:	10 days	7 days	4 days	<p>Stripe coat all crevices, welds, and sharp angles to prevent early failure in these areas.</p> <p>When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.</p> <p>Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.</p> <p>No reduction of material is recommended as it can affect film build, appearance, and adhesion.</p> <p>Do not apply the material beyond recommended pot life.</p> <p>Do not mix previously catalyzed material with new.</p> <p>In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with Reducer #54, R7K54</p> <p>Material can not be sprayed if anti-slip aggregate is use.</p> <p>Anti-slip additives, such as H&C SharkGrip®, may be added to the coating to provide some slip resistance. This product should not be used in place of a non-skid finish.</p> <p>Anti-slip additive may be mixed into the final coat just prior to application. Exception: if anti-slip is desired with Clear finish, it should be hand broadcast.</p> <p>Prime coat for concrete may be reduced up to 1 pint per gallon.</p> <p>Clear is for interior use only.</p> <p>Refer to Product Information sheet for additional performance characteristics and properties.</p>
	@ 50°F	@ 77°F	@ 120°F																														
To touch:	4 hours	2 hours	30 minutes																														
To recoat:																																	
minimum:	24 hours	8 hours	4 hours																														
maximum:	7 days	7 days	7 days																														
Foot traffic:	48 hours	24 hours	12 hours																														
Heavy Traffic hours:	4-5 days	48-72 hours	24-36																														
To cure:	10 days	7 days	4 days																														
<p>CLEAN UP INSTRUCTIONS</p>	<p>SAFETY PRECAUTIONS</p>																																
<p>Clean spills and spatters immediately with Reducer #54, R7K54. Clean tools immediately after use with Reducer #54, R7K54. Follow manufacturer's safety recommendations when using any solvent.</p>	<p>Refer to the MSDS sheet before use.</p> <p>Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.</p>																																
<p>DISCLAIMER</p>	<p>WARRANTY</p>																																
<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</p>	<p>The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.</p>																																