



ControlTech
 Tank Linings,
 Containment &
 Corrosion Control
 Coatings



TRM.88

ENVIROLASTIC® AR520 SS

PART A **B81V3500** **ISOCYANATE**
PART B **B81-3500** **SERIES**

PRODUCT INFORMATION

Revised 5/05

PRODUCT DESCRIPTION	RECOMMENDED USES
<p>ENVIROLASTIC AR520 SS is a 100% solids, slow setting, spray-applied, aromatic polyurea coating system. The slower than typical gel time allows for the introduction of mineral aggregate, colored quartz, or colored acrylic flake to provide a tough, slip-resistant, waterproof, industrial or decorative finish. It can be applied at thicknesses of 30-250 mils or greater in multiple passes during a single application.</p> <ul style="list-style-type: none"> • Fast cure, short downtime • No VOCs and low odor • Seamless, flexible and waterproof • Bridges moving cracks to 1/8" • Impact, tear and abrasion resistant • Protects against chloride intrusion • Retains physical properties at -20°F to 250°F 	<p>Designed for use as an industrial or decorative seamless floor and deck coating system for interior or exterior applications.</p> <ul style="list-style-type: none"> • Plaza decks, balconies, and walkways • Parking decks, ramps and stalls • Stadium walkways, aisles, decks and stairs • Loading docks and ramps • Institutional cafeteria, shower, and gymnasium areas • Bridge decks • Waterparks and theme parks • Marine decks, galleys and offshore • Geotextile linings • Mechanical equipment rooms • Below grade waterproofing • Acceptable in USDA inspected facilities
PRODUCT CHARACTERISTICS	PERFORMANCE CHARACTERISTICS
<p>Finish: Semi-Gloss</p> <p>Color: White, Light Gray, Medium Gray, Dark Gray, Black, Beige, Tile Red Silver Metallic, Caribbean Green</p> <p>Volume Solids: 100%</p> <p>VOC (calculated): 0</p> <p>Mix Ratio: 1:1</p> <p>Recommended Spreading Rate per application: Wet mils: 30.0 - 250.0 Dry mils: 30.0 - 250.0 Coverage: 6 - 53 sq ft/gal approximate</p> <p>Drying Schedule @ 30.0 mils wet @ 73°F and 50% RH: To touch: 3 minutes To recoat: minimum: 3 minutes maximum: 16 hours Gel time: 30 seconds Tack free: 3 minutes Light traffic: 2 hours To cure: 24 hours</p> <p><small>If maximum recoat time is exceeded, abrade surface and solvent wipe before recoating. Drying time is temperature, humidity, and film thickness dependent.</small></p> <p>Pot Life: None</p> <p>Sweat-in Time: None</p> <p>Viscosity (mixed): 550 cps</p> <p>Flash Point: 200°F</p> <p>Shelf Life: 12 months, unopened Store indoors at 70°F to 90°F.</p> <p>Reducer: Not recommended</p> <p>Clean Up: Butyl Cellusolve™ (R6K25) or Dowanol PM™</p>	<p>Abrasion Resistance Method: ASTM D4060 Result: 1000 g 1000 cycles CS-17: 9 mg loss</p> <p>Adhesion Method: ASTM D4541 Result: Concrete - 350 psi; Steel - 1,750 psi, Wood 250 psi</p> <p>Coefficient of Thermal Expansion Method: ASTM C531 (in/in/°F) Result: 4 x 10⁻⁵</p> <p>Crack Bridging (@ -26°C (-15°F) @ 1/8") Method: ASTM C836 Result: Pass</p> <p>Durometer Hardness Method: ASTM D2240 Result: Shore D-50; Shore A-95</p> <p>Gardner Impact Method: ASTM D2794 (1/32" steel panels) Result: >160 in-lbs, direct and indirect</p> <p>Mandrel Bend Method: ASTM D522 Conical Bend (1/32" steel panel) Result: Pass</p> <p>Tear Strength Method: ASTM D624 Result: 400 pli</p> <p>Tensile Elongation Method: ASTM D638 Result: 520%</p> <p>Tensile Modulus Method: ASTM D638 Result: 100% Modulus - 1,000 psi 300% Modulus - 1,600 psi</p> <p>Tensile Strength Method: ASTM D638 Result: 2,500 psi</p>



ControlTech
Tank Linings,
Containment &
Corrosion Control
Coatings



TRM.88

ENVIROLASTIC® AR520 SS

PART A **B81V3500**
PART B **B81-3500**

ISOCYANATE
SERIES

PRODUCT INFORMATION

RECOMMENDED SYSTEMS	SURFACE PREPARATION
<p>Steel Deck (pedestrian): Decorative Broadcast 1 ct. EnviroLastic AR520 SS @ 30.0 - 40.0 mils dft 1 ct. Broadcast Aggregate #5900F colored quartz @ 0.5 lbs per sq ft 1-2 cts EnviroLastic PA Clear @ 4.0 - 5.0 mils dft Concrete: Industrial Broadcast 1 ct. Corobond HS Epoxy Primer @ 3.0 - 4.0 mils dft** 1 ct. EnviroLastic AR520 SS @ 30.0 - 40.0 mils dft 1 ct. Broadcast Aggregate 40 - 60 mesh sand @ 0.5 lbs per sq ft 1-2 cts Cor-Cote HP Epoxy @ 8.0 - 10.0 mils dft/ct</p>	<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Refer to product Application Bulletin for detailed surface preparation information.</p> <p>Minimum recommended surface preparation: Steel: Atmospheric: SSPC-SP10/NACE 2, 3 mil profile Concrete & Masonry: SSPC-SP13/NACE 6 or ICRI 03732, CSP 3-5.</p>
<p>Concrete (pedestrian deck coating): 1 ct. Corobond HS Epoxy Primer @ 3.0 - 4.0 mils dft** 1 ct. EnviroLastic AR520 SS @ 30.0 - 40.0 mils dft 1 ct. Broadcast Aggregate 40 - 60 mesh sand @ 0.2 lbs per sq ft 1 ct. EnviroLastic AR200 HD @ 10.0 - 20.0 mils dft</p>	<p style="text-align: center;">TINTING</p> <p>Do not tint.</p>
<p>Concrete (vehicular deck coating): 1 ct. Corobond HS Epoxy Primer @ 3.0 - 4.0 mils dft** 1 ct. EnviroLastic AR520 SS @ 40.0 - 50.0 mils dft 1 ct. Broadcast Aggregate 40 - 60 mesh sand @ 0.2 lbs per sq ft 1 ct. EnviroLastic AR200 HD @ 10.0 - 20.0 mils dft</p>	<p style="text-align: center;">APPLICATION CONDITIONS</p> <p>Temperature: Material: 150°F minimum, 170°F maximum Air and surface: -20°F minimum, 120°F maximum At least 5°F above dew point</p> <p>Relative humidity: 80% maximum</p>
<p>Geo-Textile Lining: 1 ct. Geo-textile non-woven, 3-4oz. Amoco "Petromat"4599 1 ct. EnviroLastic AR520 SS @ 80.0 - 100.0 mils dft*</p>	<p>Refer to product Application Bulletin for detailed application information.</p> <p style="text-align: center;">ORDERING INFORMATION</p>
<p>*When used as a lining in immersion service, a minimum total dry film thickness of 60.0 mils is required.</p> <p>**Refer to Performance Tips section</p> <p>The systems listed above are representative of the product's use. Other systems may be appropriate.</p>	<p>Packaging: Part A: 53 gallon drums Part B: 53 gallon drums</p> <p style="text-align: center;">SAFETY PRECAUTIONS</p> <p>Refer to the MSDS sheet before use.</p> <p>Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.</p>
<p style="text-align: center;">DISCLAIMER</p>	<p style="text-align: center;">WARRANTY</p>
<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</p>	<p>The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.</p>



ControlTech
 Tank Linings,
 Containment &
 Corrosion Control
 Coatings



TRM.88A

ENVIROLASTIC® AR520 SS

PART A
 PART B

B81V3500
 B81-3500

ISOCYANATE
 SERIES

APPLICATION BULLETIN

Revised 5/05

SURFACE PREPARATION	APPLICATION CONDITIONS		
<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Iron & Steel (atmospheric service) Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (3 mils). Prime any bare steel the same day as it is cleaned or before flash rusting occurs.</p> <p>Poured Concrete New For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI 03732, CSP 3-5. Surface must be clean, dry, sound, and offer sufficient profile to achieve adequate adhesion. Minimum substrate cure is 28 days at 73°F. Remove all form release agents, curing compounds, salts, efflorescence, laitance, and other foreign matter by sandblasting, shotblasting, mechanical scarification, or suitable chemical means. Refer to ASTM D4260. Rinse thoroughly to achieve a final pH between 8.0 and 11.0. Allow to dry thoroughly prior to coating.</p> <p>Old Surface preparation is done in much the same manner as new concrete; however, if the concrete is contaminated with oils, grease, chemicals, etc., they must be removed by cleaning with a strong detergent. Refer to ASTM D4258. Form release agents, hardeners, etc. must be removed by sandblasting, shotblasting, mechanical scarification, or suitable chemical means. If surface deterioration presents an unacceptably rough surface, Steel-Seam VSE epoxy filler is recommended to patch and resurface damaged concrete. Fill all cracks, voids and bugholes with Steel-Seam VSE.</p> <p>Always follow the standard methods listed below: ASTM D4258 Standard Practice for Cleaning Concrete. ASTM D4259 Standard Practice for Abrading Concrete. ASTM D4260 Standard Practice for Etching Concrete. ASTM F 1869 Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete ICRI 03732 Concrete Surface Preparation</p>	<p>Temperature: Material: 150°F minimum, 170°F maximum Air and surface: -20°F minimum, 120°F maximum At least 5°F above dew point</p> <p>Relative humidity: 80% maximum</p> <tr> <th colspan="2" data-bbox="829 764 1520 806">APPLICATION EQUIPMENT</th> </tr> <p>The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.</p> <p>Reducer Not recommended</p> <p>Clean-up Butyl Cellusolve™ (R6K25) or Dowanol PM™</p> <p>Plural Component Heated Spray Equipment: Equipment Gusmer H-20/35 Gun GX7 DI, GX7-400, or GX-8 Fluid Pressure 2,200 psi Air Pressure 100 psi Inlet Strainer Screen 30 mesh Gun Screen 80 mesh</p> <p>If specific application equipment is not listed above, equivalent equipment may be substituted.</p>	APPLICATION EQUIPMENT	
APPLICATION EQUIPMENT			



ControlTech
Tank Linings,
Containment &
Corrosion Control
Coatings



TRM.88A

ENVIROLASTIC® AR520 SS

PART A **B81V3500**
PART B **B81-3500**

ISOCYANATE
SERIES

APPLICATION BULLETIN

APPLICATION PROCEDURES	PERFORMANCE TIPS
<p>Surface preparation must be completed as indicated. Route and seal all cracks greater than 1/16" with EnviroLastic JS80 SL.</p> <p>Mixing Instructions: Agitate resin blend (B) component thoroughly with a drum mixer before use to disperse pigment and assure homogeneity. Do not thin. Do not mix "A" and "B" resins together. Caution: Do not agitate in air and moisture.</p> <p>Apply coating at the recommended film thickness and spreading rate as indicated below:</p> <p>Recommended Spreading Rate per application: Wet mils: 30.0 - 250.0 Dry mils: 30.0 - 250.0 Coverage: 6 - 53 sq ft/gal approximate</p> <p>Drying Schedule @ 30.0 mils wet @ 73°F and 50% RH: To touch: 3 minutes To recoat: minimum: 3 minutes maximum: 16 hours Gel time: 30 seconds Tack free: 3 minutes Light traffic: 2 hours To cure: 24 hours</p> <p>If maximum recoat time is exceeded, abrade surface and solvent wipe before recoating. Drying time is temperature, humidity, and film thickness dependent.</p> <p>Pot Life: None</p> <p>Sweat-in Time: None</p> <p>Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.</p>	<p>For concrete, always perform Calcium Chloride test as per ASTM F1869. Do not proceed with MVE >3 lbs.</p> <p>**Where primers are used, do not fill the profile on concrete or steel with excess primer. Topcoat epoxy primers immediately after they become tack free. "Tack free" is defined as slight to medium pressure with a gloved hand, placed on a primed surface, that when lifted shows a slight imprint or distortion to the surface, with no transfer of primer to the glove.</p> <p>For steel, stripe coat all chine, welds, bolted connections, and sharp angles to prevent early failure in these areas. For concrete, all cracks must receive a 6" wide by 30 mil dft detail coat.</p> <p>Use only heated, plural component equipment capable of producing 2,500 psi at 160°F and 2 gallon/minute output consistently.</p> <p>In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with Butyl Cellusolve™ (R6K25), Dowanol PM™, or Propylene Glycol.</p> <p>While spraying, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.</p> <p>Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness or porosity of the surface, skill and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.</p> <p>Do not agitate in air and moisture.</p> <p>Consult your Sherwin-Williams representative for specific application and performance recommendations.</p> <p>Application of broadcast aggregate must be completed before material gels, in order to maintain uniform distribution and wetting of the aggregate.</p> <p>Refer to Product Information sheet for additional performance characteristics and properties.</p>
CLEAN UP INSTRUCTIONS	SAFETY PRECAUTIONS
<p>Clean spills and spatters immediately with Butyl Cellusolve™ (R6K25) or Dowanol PM™. Clean tools and equipment immediately after use (including both "A" and "B" sides of plural component spray system) with Butyl Cellusolve™ (R6K25) or Dowanol PM™.</p>	<p>Refer to the MSDS sheet before use.</p> <p>Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.</p>
DISCLAIMER	WARRANTY
<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</p>	<p>The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.</p>