



**Industrial  
&  
Marine  
Coatings**

**3.01  
WATERBORNE  
ACRYLIC DRY FALL**

**B42W1  
B42T1  
B42W2  
B42BW3**

**FLAT WHITE  
CLEAR TINT BASE (FLAT)  
EG-SHEL WHITE  
FLAT BLACK**

**PRODUCT INFORMATION**

Revised 10/06

PRODUCT DESCRIPTION		RECOMMENDED USES																									
<p><b>WATERBORNE ACRYLIC DRY FALL</b> is a water based, high light reflective white coating (black also available) that falls dry in ten feet. Fallout can be swept up for easy cleanup of work area.</p> <ul style="list-style-type: none"> <li>• High hiding</li> <li>• Increases lighting efficiency</li> <li>• High light reflectance</li> <li>• Flash rust resistance</li> <li>• Tint with EnviroToner Colorants only</li> <li>• Ten foot dry fallout</li> <li>• Easy cleanup</li> <li>• Low odor</li> <li>• Interior use</li> </ul>		<p>For use over prepared interior ceilings, walls, and structural steel in environments such as:</p> <ul style="list-style-type: none"> <li>• Warehouses</li> <li>• Industrial, commercial, and institutional buildings</li> <li>• Textile mills</li> <li>• Manufacturing facilities</li> <li>• Gymnasiums</li> <li>• Suitable for use in USDA inspected facilities</li> </ul> <p>Acceptable for use in high performance architectural applications.</p>																									
PRODUCT CHARACTERISTICS		PERFORMANCE CHARACTERISTICS																									
<p><b>Finish:</b> Flat or Eg-Shel</p> <p><b>Color:</b> Flat White, Eg-Shel White, Flat Black a wide range of colors available</p> <p><b>Volume Solids:</b> (White) 41% ± 2%</p> <p><b>Weight Solids:</b> (White) 58% ± 2%</p> <p><b>VOC (calculated):</b> &lt;100g/L; 0.83 lb/gal</p> <p><b>Recommended Spreading Rate per coat:</b></p> <p>Wet mils: 7.0 - 11.0</p> <p>Dry mils: 3.0 - 4.5</p> <p>Coverage: 135 - 225 sq ft/gal approximate</p> <p><b>Drying Schedule @ 7.0 mils wet 50% RH:</b></p> <table border="1"> <thead> <tr> <th></th> <th>@ 55°F</th> <th>@ 77°F</th> <th>@ 110°F</th> </tr> </thead> <tbody> <tr> <td>To touch:</td> <td>45 minutes</td> <td>30 minutes</td> <td>20 minutes</td> </tr> <tr> <td>To handle:</td> <td>1 hour</td> <td>45 minutes</td> <td>30 minutes</td> </tr> <tr> <td>To recoat:</td> <td>2 hours</td> <td>1 hour</td> <td>1 hour</td> </tr> <tr> <td>To cure:</td> <td>2 days</td> <td>4 hours</td> <td>3 hours</td> </tr> <tr> <td>Dry fallout:</td> <td>10-20 feet</td> <td>10 feet</td> <td>10 feet</td> </tr> </tbody> </table> <p>Drying time is temperature, humidity, and film thickness dependent.</p> <p><b>Shelf Life:</b> 36 months, unopened Store indoors at 40°F to 100°F.</p> <p><b>Flash Point:</b> 499°F, PMCC</p> <p><b>Reducer/Clean Up:</b></p> <p>Above 80°F Water</p> <p>Below 80°F 60% denatured alcohol/40% water</p>			@ 55°F	@ 77°F	@ 110°F	To touch:	45 minutes	30 minutes	20 minutes	To handle:	1 hour	45 minutes	30 minutes	To recoat:	2 hours	1 hour	1 hour	To cure:	2 days	4 hours	3 hours	Dry fallout:	10-20 feet	10 feet	10 feet	<ul style="list-style-type: none"> <li>• The bright, full-hiding, brilliant white shade of Waterborne Acrylic Dry Fall increases an area's lighting efficiency, which promotes safety and reduces eye strain due to dimly lit work stations. It helps improve employee productivity through better work area lighting due to its high light reflectance.</li> <li>• The fast drying modified acrylic resin of this waterborne coating reduces the propensity to rust, bleed, and freckle when applied over small bare steel areas, previous coating nicks, and slight rust.</li> <li>• The ten foot dry fallout characteristic reduces cleanup because its overspray dust can be swept up, thereby limiting the extent of masking equipment and floor areas. Waterborne Acrylic Dry Fall dusts less than conventional alkyd dry fall products. This helps diminish the nuisance from overspray on the applicator and the amount of waste and dust to be cleaned up.</li> <li>• Light Reflectance Value of the White is 83 ± 3% Light Reflectance Value of the Black is 5 ± 3%</li> </ul> <p><b>System Tested:</b> (unless otherwise indicated)</p> <p>Substrate: Cold rolled steel</p> <p>Surface Preparation: SSPC-SP1</p> <p>1 ct: Waterborne Acrylic Dryfall Flat @ 4.5 mils dft</p> <p><b>Abrasion Resistance:</b></p> <p>Method: ASTM D4060 CS10 wheel, 1000 cycles, 500 g load</p> <p>Result: 122 mg loss (average)</p> <p><b>Adhesion:</b> (blasted steel)</p> <p>Method: ASTM D4541</p> <p>Result: 408 psi</p> <p><b>Flexibility:</b></p> <p>Method: ASTM D522, 180° bend, 1/8" mandrel</p> <p>Result: Passes</p> <p><b>Impact Resistance:</b></p> <p>Method: ASTM D2794</p> <p>Result: Direct: 80 in. lbs. Reverse: 40 in. lbs.</p>	
	@ 55°F	@ 77°F	@ 110°F																								
To touch:	45 minutes	30 minutes	20 minutes																								
To handle:	1 hour	45 minutes	30 minutes																								
To recoat:	2 hours	1 hour	1 hour																								
To cure:	2 days	4 hours	3 hours																								
Dry fallout:	10-20 feet	10 feet	10 feet																								



**Industrial  
&  
Marine  
Coatings**

**3.01  
WATERBORNE  
ACRYLIC DRY FALL**

B42W1  
B42T1  
B42W2  
B42BW3

FLAT WHITE  
CLEAR TINT BASE (FLAT)  
EG-SHEL WHITE  
FLAT BLACK

**PRODUCT INFORMATION**

RECOMMENDED SYSTEMS	SURFACE PREPARATION
<p><b>Steel, alkyd primer:</b> 1 ct. Kem Bond HS @ 2.0-5.0 mils dft* 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Steel &amp; Rusted Galvanized, acrylic primer:</b> 1 ct. DTM Acrylic Primer/Finish @ 2.5-5.0 mils dft 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Aluminum:</b> 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Galvanized Metal:</b> 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Concrete Block:</b> 1 ct. Heavy Duty Block Filler @ 10.0-15.0 mils dft 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Poured Concrete Walls, Interior:</b> 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Plaster and Wood, Interior:</b> 1 ct. PrepRite Wall &amp; Wood Primer @ 1.5-2.0 mils dft 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Drywall:</b> 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p><b>Previously Painted:</b> 1-2 cts. Waterborne Acrylic Dry Fall @ 3.0 - 4.5 mils dft/ct</p> <p>*Steel Spec FD primers also acceptable.</p> <p>The systems listed above are representative of the product's use. Other systems may be appropriate.</p>	<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Refer to product Application Bulletin for detailed surface preparation information.</p> <p><b>Do not use hydrocarbon solvents for cleaning.</b></p> <p>Minimum recommended surface preparation: * Iron &amp; Steel: SSPC-SP2 Aluminum: SSPC-SP1 Galvanizing: SSPC-SP1 Concrete &amp; Masonry: SSPC-SP13/NACE 6, or ICRI 03732, CSP1-3 Clean, smooth, dust free * Wood: SSPC-SP1 Previously Painted * Primer required</p>
	<b>TINTING</b>
	<p>Tint with EnviroToner Colorants only. White may be tinted with up to 4 oz. per gallon. Clear Base may be tinted with up to 12 oz. per gallon. Five minutes minimum mixing on a mechanical shaker is required for complete mixing of color.</p> <p><b>Not controlled for tint strength.</b></p>
	<b>APPLICATION CONDITIONS</b>
	<p>Temperature: 50°F minimum, 110°F maximum (air, surface, and material) At least 5°F above dew point Relative humidity: 75% maximum</p> <p>Refer to product Application Bulletin for detailed application information.</p>
	<b>ORDERING INFORMATION</b>
	<p>Packaging: 5 gallon containers</p> <p>Weight per gallon: 11.58 ± 0.2 lb, may vary with color (White)</p>
	<b>SAFETY PRECAUTIONS</b>
	<p>Refer to the MSDS sheet before use.</p> <p>Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.</p>
<b>DISCLAIMER</b>	<b>WARRANTY</b>
<p>The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.</p>	<p>The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.</p>



**Industrial  
&  
Marine  
Coatings**

**3.01A  
WATERBORNE  
ACRYLIC DRY FALL**

B42W1  
B42T1  
B42W2  
B42BW3

FLAT WHITE  
CLEAR TINT BASE (FLAT)  
EG-SHEL WHITE  
FLAT BLACK

**APPLICATION BULLETIN**

Revised 10/06

SURFACE PREPARATION	APPLICATION CONDITIONS
<p>Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.</p> <p>Do not use hydrocarbon solvents for cleaning.</p> <p><b>Iron &amp; Steel</b> Minimum surface preparation is Hand Tool Clean per SSPC-SP2. Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. For better performance, use Commercial Blast Cleaning per SSPC-SP6/NACE 3, blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (2 mils). Prime any bare steel within 8 hours or before flash rusting occurs. Primer required.</p> <p><b>Aluminum</b> Remove all oil, grease, dirt, oxide and other foreign material by Solvent Cleaning per SSPC-SP1.</p> <p><b>Galvanized Steel</b> Remove all oil, grease, dirt, oxide and other foreign material by Solvent Cleaning per SSPC-SP1. When the surface has been treated with chromates or silicates, first Solvent Clean per SSPC-SP1 and apply a test patch. Allow paint to dry at least one week before testing adhesion. If adhesion is poor, brush blasting per SSPC-SP7 is necessary to remove these treatments. Rusty galvanizing requires a minimum of Hand Tool Cleaning per SSPC-SP2, prime the area the same day as cleaned.</p> <p><b>Concrete and Masonry</b> For surface preparation, refer to SSPC-SP13/NACE 6, or ICRI 03732, CSP 1-3. Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, dirt, form release agents, moisture curing membranes, loose cement and hardeners. Concrete and mortar must be cured at least 28 days @ 75°F. On tilt-up and poured-in-place concrete, commercial detergents and abrasive blasting may be necessary. Fill bug holes, air pockets and other voids with ArmorSeal Crack Filler. Primer required. Brick must be allowed to weather for one year prior to surface preparation and painting.</p> <p><b>Drywall</b> Must be clean and dry. All nail heads must be set and spackled. Joints must be taped and covered with joint compound. Spackled nail heads and tape joints must be sanded smooth and all dust removed prior to the application of paint.</p> <p><b>Wood</b> Surface must be clean, dry and sound. Prime with recommended primer and paint as soon as possible. Knots and pitch streaks must be scraped, sanded and spot primed before full coat of primer is applied. All nail holes or small openings must be properly caulked.</p>	<p>Temperature: 50°F minimum, 110°F maximum (air, surface, and material) At least 5°F above dew point</p> <p>Relative humidity: 75% maximum</p> <p><b>NOTE:</b> Dryfall characteristics will be adversely affected at temperatures below 77°F or above 50% relative humidity.</p>
<b>APPLICATION EQUIPMENT</b>	
<p>The following is a guide. Changes in pressures and tip sizes may be needed for proper spray characteristics. Always purge spray equipment before use with listed reducer. Any reduction must be compliant with existing VOC regulations and compatible with the existing environmental and application conditions.</p> <p><b>Reducer/Clean Up:</b> Above 80°F ..... Water Below 80°F ..... 60% denatured alcohol/40% water</p> <p><b>Airless Spray</b> Pressure ..... 2800 Hose ..... 1/4" ID Tip ..... .017"-.019" Filter ..... 60 mesh Reduction ..... Not recommended</p> <p><b>Conventional Spray</b> Gun ..... Binks 95 Fluid Nozzle ..... 63C Air Nozzle ..... 63PB Atomization Pressure ... 60 psi Fluid Pressure ..... 50 psi Reduction ..... As needed up to 10% by volume</p> <p><b>Brush</b> Brush ..... Not recommended</p> <p><b>Roller</b> Cover ..... Not recommended</p> <p>If specific application equipment is not listed above, equivalent equipment may be substituted.</p>	



**Industrial  
&  
Marine  
Coatings**

# 3.01A WATERBORNE ACRYLIC DRY FALL

B42W1  
B42T1  
B42W2  
B42BW3

FLAT WHITE  
CLEAR TINT BASE (FLAT)  
EG-SHEL WHITE  
FLAT BLACK

## APPLICATION BULLETIN

### APPLICATION PROCEDURES

Surface preparation must be completed as indicated.

Mix paint thoroughly by boxing and stirring before use.

Apply paint at the recommended film thickness and spreading rate as indicated below:

**Recommended Spreading Rate per coat:**

Wet mils:	7.0 - 11.0
Dry mils:	3.0 - 4.5
Coverage:	135 - 225 sq ft/gal approximate

**Drying Schedule @ 7.0 mils wet 50% RH:**

	@ 55°F	@ 77°F	@ 110°F
To touch:	45 minutes	30 minutes	20 minutes
To handle:	1 hour	45 minutes	30 minutes
To recoat:	2 hours	1 hour	1 hour
To cure:	2 days	4 hours	3 hours
Dry fallout:	10-20 feet	10 feet	10 feet

Drying time is temperature, humidity, and film thickness dependent.

Application of coating above maximum or below minimum recommended spreading rate may adversely affect coating performance.

### PERFORMANCE TIPS

When using spray application, use a 50% overlap with each pass of the gun to avoid holidays, bare areas, and pinholes. If necessary, cross spray at a right angle.

During the early stages of drying, the coating is sensitive to rain, dew, high humidity and moisture condensation. Plan painting schedules to avoid these influences during the first 16-24 hours of curing.

Spreading rates are calculated on volume solids and do not include an application loss factor due to surface profile, roughness, or porosity of the surface, skill, and technique of the applicator, method of application, various surface irregularities, material lost during mixing, spillage, overthinning, climatic conditions, and excessive film build.

Reduction will have an adverse effect on the dryfall and flash rust characteristics of this coating.

Dryfall characteristics will be adversely affected at temperatures below 77°F or above 50% relative humidity.

In order to avoid blockage of spray equipment, clean equipment before use or before periods of extended downtime with water.

Overspray landing on hot surfaces may adhere to these surfaces. Immediately remove overspray from hot surfaces before adhesion occurs. Note that surface temperatures can be higher than air temperature.

Use EnviroToner Colorants only at the recommended levels.

Refer to Product Information sheet for additional performance characteristics and properties.

### CLEAN UP INSTRUCTIONS

Clean spills and splatters immediately with soap and warm water. Clean tools immediately after use with soap and warm water. After cleaning, flush spray equipment with Mineral Spirits, R1K4, to prevent rusting of equipment. Follow manufacturer's safety recommendations when using any solvent.

### SAFETY PRECAUTIONS

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

### DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

### WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.